

Diesel / Gasoil

Date of sampling: 28.05.2017

Samples taken by: independent inspectors

TEST	UNIT	METHOD	RESULT
Ash	Wt %	ISO 6245	< 0.01
Carbon residue (10%)	Wt %	ISO 10370	< 0.10
Cetane index	-	ISO 4264	54.4
Cetane number	-	EN 15195	53.9
Cloud point	°C	EN 23015	- 4
Cold filter plugging point	°C	EN 116	- 18
Colour (ASTM)	-	ISO 2049	-
Conductivity	pS/m	ASTM D2624	365
Copper corrosion (3 hrs at 50°C)	rating	ISO 2160	1a
Density at 15°C	kg/m ³	ISO 12185	831.4
Dist: Recovered at 250°C	% v	ISO 3405	31.5
Dist: Recovered at 350°C	% v	EN ISO 3405	93.5
Flash point	°C	ISO 2719	66.0
Lubricity	µm	ISO 12156-1	409
Oxidation stability	g/m ³	EN ISO 12205	-
Sulphur content	mg/kg	ISO 20846	8.2
Viscosity at 40°C	CST	ISO 3104	2.812
Water content	mg/kg	EN ISO 12937	50