

# Diesel / Gasoil

**Date of sampling: 20.06.2019**

**Samples taken by: independent inspectors**

TEST	UNIT	METHOD	RESULT
Ash	% m/m	ISO 6245	0.001
Carbon residue (10%)	% m/m	EN ISO 10370	< 0.10
Cetane index	-	EN ISO 4264	55.1
Cetane number	-	EN ISO 5165	52.3
Cloud point	°C	EN 23015	- 7
Cold filter plugging point	°C	EN 116	- 16
Colour (ASTM)	-	ISO 2049	0.5
Conductivity	pS/m	ISO 6297	214
Copper corrosion (3 hrs at 50°C)	rating	ISO 2160	1a
Density at 15°C	kg/m <sup>3</sup>	EN ISO 12185	0.8319
Dist: Recovered at 250°C	% v/v	EN ISO 3405	33.0
Dist: Recovered at 350°C	% v/v	EN ISO 3405	94.0
Flash point	°C	ISO 2719 A	56.0
Lubricity	µm	EN ISO 12156-1	424
Oxidation stability	g/m <sup>3</sup>	EN ISO 12205	7
Sulphur content	mg/kg	EN 20846	5.9
Viscosity at 40°C	CST	EN ISO 3104	2.766
Water content	mg/kg	EN ISO 12937	42