

Unleaded Petrol

Date of sampling: 20.07.2017

Samples taken by: independent inspectors

TEST	UNIT	METHOD	RESULT
Appearance		Visual	Clear & bright
RON		IP 237	95.0
MON		IP 236	85.0
Density at 15°C	kg/m ³	IP 365	745.2
Lead	mg/l	IP 428	< 2.5
Sulphur content	mg/kg	IP 490	3.1
Copper corrosion 3 hrs at 50°C		IP 154	1a
Benzene	% (v/v)	IP 429	0.9
M.T.B.E	% (v/v)	IP 466	< 0.2
E.T.B.E	% (v/v)	IP 466	< 0.2
Methanol	% (v/v)	IP 466	0.4
Ethanol	% (v/v)	IP 466	3.9
Iso-Propanol	% (v/v)	IP 466	< 0.2
Sec-Butanol	% (v/v)	IP 466	< 0.2
T.A.M.E	% (v/v)	IP 466	< 0.2
Tert-Butanol	% (v/v)	IP 466	< 0.2
Iso-Butanol	% (v/v)	IP 466	< 0.2
Oxygen content	% (m/m)	IP 466	1.64
Vapour pressure	kPa	IP 394	69.9
I.B.P	°C	EN ISO 3405	29.9
10% v rec. at	°C	EN ISO 3405	45.8
50% v rec. at	°C	EN ISO 3405	87.4
90% v rec. at	°C	EN ISO 3405	156.7
F.B.P	°C	EN ISO 3405	197.2
% v evap. at 70°C	% (v/v)	EN ISO 3405	40.1
% v evap. at 100°C	% (v/v)	EN ISO 3405	56.8
% v evap. at 150°C	% (v/v)	EN ISO 3405	87.5
Aromatics	% (v/v)	IP 156	31.5
Olefins	% (v/v)	IP 156	6.4